Figure: 30 TAC §115.473(e)

Table 1.	
<u>Application Specific Adhesives[Category]</u>	Grams of volatile organic compounds (VOC) per liter adhesive
Architectural Applications	
<u>Building Envelope Membrane</u> <u>Adhesive</u>	<u>250</u>
Carpet Pad Adhesive	<u>50</u>
Ceramic Tile Installation Adhesive	<u>65</u>
Cove Base Installation Adhesive	<u>50</u>
Dry Wall Adhesive	<u>50</u>
<u>Glass, Porcelain, and Stone Tile</u> <u>Adhesive</u>	<u>65</u>
Multipurpose Construction Adhesive	<u>70</u>
<u>Panel Adhesive</u>	<u>50</u>
Roofing	
<u>Hot Applied Modified Bitumen or</u> <u>Built Up Roof Adhesive</u>	<u>30</u>
<u>EPDM/TPO Single-Ply Roof Membrane</u> <u>Adhesive</u>	<u>250</u>
<u>Single-Ply Roof Membrane</u> <u>Installation and Repair Adhesive</u> (Except EPDM and TPO)	<u>250</u>
Shingle Laminating Adhesive	<u>30</u>
All Other Roof Adhesives	<u>250</u>
Rubber Floor Adhesive	<u>60</u>
Structural Glazing Adhesive	<u>100</u>
Structural Wood Member Adhesive	<u>140</u>
Subfloor Adhesive	<u>50</u>
VCT and Asphalt Tile Adhesive	<u>50</u>
Wood Flooring Adhesive	<u>20</u>
All Other Indoor Floor Covering Adhesives	<u>50</u>
All Other Outdoor Floor Covering Adhesives	<u>50</u>
Computer Diskette Manufacturing Adhesive	350
Contact Adhesive	80
Edge Glue	250
Plastic Welding Cement	
ABS Welding Cement	325
ABS to PVC Transition Cement	<u>425[</u> 510]
CPVC Welding Cement	<u>400[</u> 490]

Table 1.	
<u>Application Specific Adhesives[Category]</u>	Grams of volatile organic compounds (VOC) per liter adhesive
CPVC For Life-Safety Systems	490
Higher Viscosity CPVC Welding Cement	<u>400</u> [490]
PVC Welding Cement	<u>425[</u> 510]
All Other Plastic Welding Cements	100
Rubber Vulcanization Adhesive	<u>250[</u> 850]
Special Purpose Contact Adhesive	250
Thin Metal Laminating Adhesive	780
Tire Tread Adhesive	100
Top and Trim Adhesive	<u>250[</u> 540]
Waterproof Resorcinol Glue	170
All Other Adhesives	250

Table 2.	
Substrate Specific Adhesives	Grams of volatile organic compounds (VOC) per liter adhesive
Metal	30
Plastic Foams	50
Porous Material (except wood)	50
Wood	30
Fiberglass	80
Reinforced Plastic Composite	200

Table 3.	
Adhesive Primers	Grams of volatile organic compounds (VOC) per liter adhesive
Plastic	550
Pressure Sensitive	785
Traffic Marking Tape	150
Vehicle Glass	700
Roof Adhesive Primers	250
All Other Adhesive Primers	250